## **REMARKS**

Applicants respectfully request that the present amendments be entered. It is believed that the present amendments place the application in condition for allowance.

Respectfully Submitted,

FAY, SHARPE, FAGAN, MINNICH & McKEE, LLP

Richard M. Klein Reg. No. 33,000 Mark E. Bandy Reg. No. 35,788 1100 Superior Avenue, 7th Floor Cleveland, Ohio 44114-2518 (216) 861-5582

L:\DBC\DATA\MR\SLD20353.PLA

## **VERSION WITH MARKINGS TO SHOW CHANGES MADE**

## **IN THE SPECIFICATION:**

The paragraph starting on page 1, line 1 has been replaced with the following paragraph:

--This application is a continuation of U.S. Application Serial No.

## IN THE CLAIMS:

The present claims have been amended as follows:

- 2. (Amended) A golf ball according to claim 1, wherein the inner cover layer has a thickness of about 0.100 to about 0.010 inches and the outer cover layer has a thickness of about 0.010 to about [0.70] 0.070 inches, the golf ball having the properties required by the U.S.G.A. and having an overall diameter of 1.680 inches or more.
- 3. (Amended) A golf ball according to claim 1 wherein the inner cover layer has a thickness of about 0.050 inches and the outer cover layer has a thickness of about 0.055 inches, the golf ball having the properties required by the U.S.G.A. and having an overall diameter of 1.680 inches or more.
  - [8.] <u>6.</u> (Amended) A multi-layer golf ball comprising: a spherical core;

an inner cover layer molded over said spherical core to form a spherical intermediate ball, said inner cover layer comprising an ionomeric resin having no more than 16% by weight of an alpha, beta-unsaturated carboxylic acid and having a modulus of from about 15,000 to about 70,000 psi;

an outer cover layer molded over said spherical intermediate ball to form a multi-layer golf ball, the outer layer comprising a non-ionomeric elastomer selected from the group consisting of polyester elastomer, polyester, polyether polyurethane and polyester amide, said outer cover layer having a modulus in a range of about 1,000 to about 30,000 psi.